



## QUALITEK<sup>®</sup> SUPER DEOX SD #1 AND SD #1H

**CORPORATE HEADQUARTERS** USA: 315 Fairbank St. Addison, IL • 630-628-8083 • FAX 630-628-6543  
**EUROPE** UK: Unit 9 Apex Ct. Bassendale Rd. Bromborough, Wirral CH62 3RE • 44 151 334 0888 • FAX 44 151 346 1408  
**ASIA-PACIFIC HEADQUARTERS** SINGAPORE: 6 Tuas South St. 5 Singapore 637790 • 65 6795 7757 • FAX 65 6795 7767  
**PHILIPPINES:** Phase 1 Qualitek Ave. Mariveles, Bataan Philippines C-2106 • 6347 935 4163 • FAX 63475613717  
**CHINA:** 3B/F, YiPa Print Bldg. 351 # JiHua Rd., Buji Shenzhen, China 518112 • 86 755 28522814 • FAX 86 755 28522787

**Description**

Super Deox #1 and Super Deox #1H both consist of white powder formulated to reduce and prevent oxide formation of solder, known as dross. Super Deox #1 and #1H may be used on wave soldering equipment as well as still solder pots. Both SD #1 and #1H are stable, low fuming powders with no flash points. Other dross-reducing agents contain mineral oils and fatty acid compounds that breakdown and may deposit on printed circuit board assemblies. Super Deox #1H has been formulated specifically for oxide reduction of high temperature, lead-free alloys (>200 °C).

Main Features

- Powder-form dross reducer
- Low fuming
- High Temperature Lead-Free version available
- Reduces alloy waste

**Technical Data**

	<b>Specification</b>
<b>Color and Appearance</b>	White Crystalline Powder
<b>Flash Point</b>	None
<b>Shelf Life</b>	3 years from DOM

**Application**

Before use, the wave must be turned off. Sprinkle either Super Deox #1 or Super Deox #1H over the surface about 1/8 inch in thickness. Use a spoon or spatula to gently mix the Super Deox with the solder. SD #1 and SD #1H will move to the surface of the solder and react with the oxides of the solder, converting them back into their metallic state.

**Recommended Solder Pot Temperatures**

**Super Deox #1**

450 – 485 °F (232 – 252 °C)

**Super Deox #1H**

Sn96.5/Ag3.5	500 – 530 °F (260 – 276 °C)
Sn95/Ag5	536 – 565 °F (280 – 296 °C)
Sn99.3/Cu0.7	510 – 530 °F (265 – 276 °C)
Sn/Ag/Cu	520 – 530 °F (271 – 276 °C)
Sn95/Sb5	536 – 565 °F (280 – 296 °C)

**Storage & Shelf Life**

Super Deox should be stored in cool, dry environment. Shelf life is 3 years from date of manufacture.

**Packaging**

Super Deox #1 and Super Deox #1H are available in 1, 10, 25 and 50 lb. containers.

**Disposal**

Super Deox #1 and #1H contain hazardous ingredients so should be disposed of in accordance with federal, state and local authority requirements.

Qualitek® is a brand of Qualitek International, Inc. For Health and Safety Information, refer to Safety Data Sheet.