



NC601 (Sn/Ag/Cu)
NO CLEAN DELTA®
SOLDER WIRE

CORPORATE HEADQUARTERS USA: 315 Fairbank St. Addison, IL † 630-628-8083 FAX 630-628-6543

EUROPE UK: Unit 9 Apex Ct. Bassendale Rd. Bromborough, Wirral CH62 3RE † 44 151 334 0888 † FAX 44 151 346 1408

ASIA-PACIFIC HEADQUARTERS SINGAPORE: 6 Tuas South St. 5 Singapore 637790 † 65 6795 7757 † FAX 65 6795 7767

PHILIPPINES: Phase 1 Qualitek Ave. Mariveles, Bataan Philippines C-2106 † 6347 935 4163 † FAX 63475613717

CHINA: 3B/F, YiPa Print Bldg. 351 # JiHua Rd., Buji Shenzhen, China 518112 † 86 755 28522814 † FAX 86 755 28522787

This data is based on information that the manufacturer believed to be reliable and offered in good faith. Qualitek International, Inc. makes no warranties expressed or implied as to its accuracy and assumes no responsibilities and liabilities arising out of its use by others as conditions and methods of use of the products is beyond the control of Qualitek International, Inc. The user must determine the suitability of the product before using it on a commercial basis. The warranties extend only to the conformity of the product to the physical descriptions. In no event will Qualitek International, Inc. be responsible for special, incidental and consequential damages whether the claim is in contract, negligence or otherwise. Qualitek specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.

Description

Flux Core

Delta Solder Wire NC601 is a no clean cored solder wire that is available with both lead-containing alloys and lead-free tin/silver copper alloys, such as SAC305 and SAC405. It provides the fluxing activity levels that promote fast wetting action and maximum wetting spread. NC601 contains purely organic acid activators so leaves minimal residue and spreads like an RA type cored solder wire. NC601 exhibits virtually no spattering and conforms to IPC-J-STD-004B.

Main Features

- Excellent wettability
- Non-tacky residue
- RoHs Compliant

Technical Data (Flux Extract)

	Specification	Test Method
Color & Appearance	Light yellow solid	Visual
Flux Classification	ORLO	J-STD-004
Copper Mirror	No removal of copper film	IPC-TM-650 2.3.32
Silver Chromate	Pass	IPC-TM-650 2.3.33
Corrosion	Pass	IPC-TM-650 2.6.15
SIR		
JSTD-004, Pattern Down	2.33 x 10 ¹¹	IPC-TM-650 2.6.3.3
Bellcore (Telecordia)	6.12 x 10 ¹¹ ohms	Bellcore GR-78-CORE 13.1.3
Electromigration	Pass	Bellcore GR-78-CORE 13.1.4
Post Reflow Flux Residue	55%	TGA Analysis
Acid Value (mgKOH/g)	280 - 330	IPC-TM-650 2.3.13
Spitting of Flux-Cored Solder	0.3%	IPC-TM-650 2.4.48
Solder Spread	130 mm ²	IPC-TM-650 2.4.46

Wire Diameter

Delta Solder Wire NC601 with tin/silver copper alloys is available in a variety of diameters. The chosen diameter is based on application methods, pad size, and desired solder joint volume. Generally, the diameter of the wire should be slightly larger than the width/diameter of the joint or connection to be soldered. Below is a list of standard diameters.

Standard wire diameters

Diameter/Inch	0.125	0.092	0.062	0.050	0.040	0.032	0.028	0.025	0.020	0.015	0.010
Diameter/mm	3.18	2.33	1.57	1.27	1.01	0.81	0.71	0.63	0.51	0.38	0.25
Std.Wire Gauge	11	13	16	18	19	21	22	23	25	28	31
Tolerance, in.	+/-0.006	+/-0.005	+/-0.003	+/-0.003	+/-0.002	+/-0.002	+/-0.002	+/-0.002	+/-0.002	+/-0.002	+/-0.002

Flux Percentage

Qualitek utilizes a state-of-the-art automatic wire extrusion and wire drawing machines to manufacture consistent solder. The introduction of flux core in the wire extrusion process involves continual monitoring of flux percentage to ensure minimal flux voids and irregular wire. Typical flux percentage for high temperature lead-free SAC-containing alloy solder is **1.1 – 3.3%**.

Physical Properties

Solder Composition

Qualitek has developed a no clean organic based core flux with tin/silver/copper (SAC) alloys. Qualitek SAC alloys conform to and exceed the impurity requirements of IPC-J-STD-006C.

Typical Analysis														
	Sn	Ag	Cu	Pb	Sb	Bi	In	As	Fe	Ni	Cd	Al	Zn	Au
LF955-38	Bal	3.6-4.0	0.5-0.9	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max
LF958-35	Bal	3.3-3.7	0.5-0.9	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max
LF965-30	Bal	2.8-3.2	0.3-0.7	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max
LF217	Bal	3.8-4.2	0.3-0.7	0.070 Max	0.200 Max	0.100 Max	0.100 Max	0.030 Max	0.020 Max	0.010 Max	0.002 Max	0.005 Max	0.003 Max	0.050 Max

	Sn/Ag/Cu	Sn63/Pb37
Melting Point, °C	217-221	183 E
Hardness, Brinell	15HB	14HB
Coefficient of Thermal Expansion	Pure Sn= 23.5	24.7
Tensile Strength, psi	4312	4442
Density, g/cc	7.39	8.42
Electrical Resistivity , (μohm-cm)	13.0	14.5
Electrical Conductivity, %IACS	16.6	11.9

	Sn/Ag/Cu	Sn63/Pb37
Yield Strength, psi	3724	3950
Total Elongation,%	27	48
Joint Shear Strength, at 0.1mm/min 20 °C	27	23
Joint Shear Strength, at 0.1mm/min 100 °C	17	14
Creep Strength, N/mm ² at 0.1mm/min 20 °C	13.0	3.3
Creep Strength, N/mm ² at 0.1mm/min 100 °C	5	1
Thermal Conductivity, W/m.K	58.7	50.9

Flux Residues & Cleaning

NC601 is a no clean formulation; therefore, residue removal is not required for typical applications. If residue removal is desired, the use of Everkleen 1005 Buffered Saponifier with a 5-15% concentration in hot 60 °C (140 °F) de-ionized water will aid in residue removal.

Storage & Shelf Life

Solder wire storage should be in a 65-80 °F environment away from direct heat. We recommend using gloves when handling solder wire directly. Solder wire has an indefinite shelf life.

Disposal

SAC alloy NC601 lead-free solder should be disposed of in accordance with federal, state & local authority requirements.

Packaging

Qualitek flux-core wire and solid wire are packed in

- 12.5lb -box of ½ lb spools
- 25 lb -box of 1 lb spools
- 12.5kg -box of ½ kg spools
- 8 kg -box of 1kg spools
- 40 lb -box of 5 lb spools
- 20 lb -box of 20 lb spools